

## 3/4" Corrugated Load Table

Allowable Uniform Loads In Pounds Per Square Foot

### Span Length

Thickness	# Spans	4'	4' 6"	5'	5' 6"	6'	6' 6"	7'	7' 6"	8'	8' 6"	9'	9' 6"	10'
18 Ga	1	107	85	69	57	48	41	35	31	27	24	21	-	-
	3	134	106	86	71	60	51	44	38	34	30	27	24	22
20 Ga	1	82	64	52	43	36	31	27	23	20	-	-	-	-
	3	102	81	65	54	45	39	33	29	26	23	20	-	-
22 Ga	1	92	73	59	49	41	35	30	26	23	20	-	-	-
	3	115	91	74	61	51	44	38	33	29	26	23	20	-
24 Ga	1	74	59	48	39	33	28	24	21	-	-	-	-	-
	3	93	73	59	49	41	35	30	26	23	21	-	-	-
26 Ga	1	56	44	36	30	25	21	-	-	-	-	-	-	-
	3	70	55	45	37	31	27	23	20	-	-	-	-	-

*Stress governing, 37 ksi yield for 18, 20 Ga; 50 ksi for 22, 24 and 26 Ga*